

## TASSO Grade EN-GJL-200C (According to EN 16482:2014)

This grade offers exceptional machinability and excellent surface finishes, but limited strength and wear resistance. Noise and vibration damping are excellent in this grade.

Main Elements: Iron, Carbon, Silicon, Manganese, Phosphorous, Sulphur, Others/Alloying

Denstiy: 7,25 gr/cm3

	Tensile Strength (Mpa) (20 C)	Hardness
20 – 50 mm	155	140 - 210 HRB
50 - 100 mm	140	140 - 210 HRB
100 – 200 mm	125	140 - 210 HRB
200 – 400 mm	115	140 - 210 HRB